

KB-5152 (相当于 GB: 22F)

布、纸组合覆铜基板

Features 特点

- Excellent punching property, Suitable for punching at 45°C~70°C
优异的冲孔性，最佳冲孔温度为 45°C~70°C
- IPC-4101E/10 specification is applicable.
符合 IPC-4101E/10 的规范要求
- Plated through holes are not recommended for the cellulose core is easily attacked by the electrolyte
不适应 PTH 制程

Applications 应用领域

- Display
显示器
- VCR
录像机
- Power supply
电源基板
- Industrial Instrument
工业仪表
- Digital sound recorder, etc
数码刻录机等

General Properties 一般特性

Test Item 测试项目	Unit 单位	Test Method (IPC-TM-650) 测试方法	Test Condition 处理条件	Specification (IPC-4101E) 规范值	Typical Value 典型值
Thermal 热性能					
Solder Resistance 耐焊性	Sec	2.4.13.1	Float 260°C/unetched	≥10	20
Flammability 燃烧性	Rating	UL94	UL-94	-	V-0/V-1
Electrical 电性能					
Surface Resistivity 表面电阻	MΩ	2.5.17.1	C-96/35/90	≥1.0×10 ⁴	1.0×10 ⁶
Volume Resistivity 体积电阻	MΩ-cm	2.5.17.1	C-96/35/90	≥1.0×10 ⁶	1.0×10 ⁸
Dielectric Constant 介电常数	—	2.5.5.2	Etched/@1 MHz	≤5.4	4.6
Loss Tangent 介质损耗	—	2.5.5.2	Etched/@1 MHz	≤0.035	0.023
Arc Resistance 耐电弧性	Sec	2.5.1	D-48/50+D-0.5/23	≥60	125
Comparative Tracking Index 相比漏电起痕指数	V	IEC 60112	Etched/0.1% NH ₄ CL	≥175	175
Mechanical 机械性能					
Peel Strength (1 oz.) 铜箔剥离强度	N/mm	2.4.8	125°C	AABUS	1.4-1.6
			Float 260°C / 10 Sec	AABUS	1.4-1.6
Bow / Twist 弯弓度/翘曲度	%	2.4.22.1	A	≤1.5	0.35/0.5
Flexural Strength 抗弯强度	N/mm ²	2.4.4	Lenth direction	≥242	300
			Cross direction	≥172	240
Moisture Absorption 吸水率	%	2.6.2.1	D-24/23	≤0.5	0.25

Remarks:

Specimen Thickness: 1.6mm 1/0 样品厚度：1.6mm 1/0

A = Keep the specimen originally without any process 保持原样,不作处理

C = Temperature and humidity conditioning 在恒温恒湿的空气中处理

D = Immersing in distilled water with temperature control 浸在恒温的水中处理

E = Temperature conditioning 在恒温的空气中处理